



# IS410

## Lead-free Epoxy Laminate and Prepreg

IS410 is a high-performance FR-4 epoxy laminate and prepreg system designed to support the printed circuit board industry's requirements for higher levels of reliability and the trend to use lead-free solder.

Isola's IS410 has a glass transition temperature (Tg) of 180°C and is specially formulated for superior performance through multiple thermal excursions, passing 6X solder tests at 288°C. IS410 is optimized for enhanced drilling performance allowing high aspect ratio holes of  $\leq 10$  mils. Its unique resin chemistry provides CAF resistance with the benefit of long-term reliability of boards built with small feature designs.

### Product Attributes

Legacy Materials

### Typical Market Applications

Aerospace & Defense , Consumer Electronics , Networking & Communication Systems , Medical, Industrial & Instrumentation , Automotive & Transportation

#### ORDERING INFORMATION:

Contact your local sales representative or visit [www.isola-group.com](http://www.isola-group.com) for further information.

Isola Group  
3100 West Ray Road  
Suite 301  
Chandler, AZ 85226  
Phone: 480-893-6527  
Fax: 480-893-1409  
[info@isola-group.com](mailto:info@isola-group.com)

Isola Asia Pacific (Hong Kong) Ltd.  
Unit 3512 - 3522, 35/F  
No. 1 Hung To Road, Kwun Tong,  
Kowloon, Hong Kong  
Phone: 852-2418-1318  
Fax: 852-2418-1533  
[info.hkg@isola-group.com](mailto:info.hkg@isola-group.com)

Isola GmbH  
Isola Strasse 2  
D-52348 Düren,  
Germany  
Phone: 49-2421-8080  
Fax: 49-2421-808164  
[info-dur@isola-group.com](mailto:info-dur@isola-group.com)

# Data Sheet

Tg 180°C

Td 350°C

Dk 3.97

Df 0.02

IPC-4101/21 /24 /26 /121 /124 /129

UL - File Number E41625

Last Updated December 15, 2017  
Revision No: 5

### Product Features

- Industry Recognition
  - UL File Number: E41625
  - RoHS Compliant
- Performance Attributes
  - Lead-free assembly compatible
  - 6x 288°C solder float capable
- Processing Advantages

### Product Availability

- Standard Material Offering: Laminate
  - 2 to 125 mil (0.05 to 3.2 mm)
  - Available in full size sheet or panel form
- Copper Foil Type
  - HTE Grade 3
  - RTF (Reverse Treat Foil)
- Copper Weight
  - ½ to 2 oz (18 to 70  $\mu$ m) available
  - Heavier copper available
  - Thinner copper foil available
- Standard Material Offering: Prepreg
  - Roll or panel form
  - Tooling of prepreg panels
- Glass Fabric Availability
  - E-glass
  - Square weave glass

| Property   | Typical Value  | Units   | Test Method   |
|--|--|---|---|
|  |  | Metric (English)                                      | IPC-TM-650 (or as noted)  |
| Glass Transition Temperature (Tg) by DSC               | 180  | °C  | 2.4.25C   |
| Decomposition Temperature (Td) by TGA @ 5% weight loss | 350  | °C  | 2.4.24.6  |
| Time to Delaminate by TMA (Copper removed)             | A. T260<br>B. T288   | 50<br>10  | Minutes<br>2.4.24.1   |
| Z-Axis CTE   | A. Pre-Tg<br>B. Post-Tg<br>C. 50 to 260°C, (Total Expansion)   | 55<br>250<br>3.5                                      | ppm/°C<br>ppm/°C<br>%<br>2.4.24C<br>2.4.24C   |
| X/Y-Axis CTE   | Pre-Tg   | 11  | ppm/°C<br>2.4.24C   |
| Thermal Conductivity                                   |  | 0.5   | W/mK<br>ASTM E1952  |
| Thermal Stress 10 sec @ 288°C (550.4°F)                | A. Unetched<br>B. Etched   | Pass  | Pass Visual<br>2.4.13.1   |
| Dk, Permittivity                                       | A. @ 100 MHz<br>B. @ 1 GHz<br>C. @ 2 GHz<br>D. @ 5 GHz<br>E. @ 10 GHz  | 3.96<br>3.90<br>3.97<br>3.87<br>3.87                  | —<br>2.5.5.3<br>2.5.5.9<br>Bereskin Stripline<br>Bereskin Stripline<br>Bereskin Stripline |
| Df, Loss Tangent                                       | A. @ 100 MHz<br>B. @ 1 GHz<br>C. @ 2 GHz<br>D. @ 5 GHz<br>E. @ 10 GHz  | 0.0149<br>0.0189<br>0.0200<br>0.0230<br>0.0230        | —<br>2.5.5.3<br>2.5.5.9<br>Bereskin Stripline<br>Bereskin Stripline<br>Bereskin Stripline |
| Volume Resistivity                                     | A. After moisture resistance<br>B. At elevated temperature   | 8.0 x 10 <sup>8</sup><br>3.6 x 10 <sup>8</sup>        | MΩ-cm<br>2.5.17.1   |
| Surface Resistivity                                    | A. After moisture resistance<br>B. At elevated temperature   | 8.0 x 10 <sup>6</sup><br>4.5 x 10(8)                  | MΩ<br>2.5.17.1  |
| Dielectric Breakdown                                   |  | >50   | kV  |
| Arc Resistance   |  | 129   | Seconds   |
| Electric Strength (Laminate & laminated prepreg)       |  | 44 (1100)   | kV/mm (V/mil)   |
| Comparative Tracking Index (CTI)                       |  | 3 (175-249)   | Class (Volts)<br>UL 746A<br>ASTM D3638  |
| Peel Strength  | A. Low profile copper foil and very low profile copper foil all copper foil >17 μm [0.669 mil]<br>B. Standard profile copper<br>1. After thermal stress<br>2. At 125°C (257°F)<br>3. After process solutions | 1.14 (6.5)<br>1.225 (7.0)<br>1.14 (6.5)<br>0.90 (5.1) | N/mm (lb/inch)<br>2.4.8C<br>2.4.8.2A<br>2.4.8.3<br>2.4.8.3                                |
| Flexural Strength                                      | A. Length direction<br>B. Cross direction  | 82,600<br>66,400                                      | 2.4.4B  |
| Tensile Strength                                       | A. Length direction<br>B. Cross direction  | 60,890<br>45,750                                      | ASTM D3039  |
| Poisson's Ratio  | A. Length direction<br>B. Cross direction  | 0.175<br>0.143  | —<br>ASTM D3039   |
| Moisture Absorption                                    |  | 0.20  | %<br>2.6.2.1A   |
| Flammability (Laminate & laminated prepreg)            |  | V-0   | Rating<br>UL 94   |
| Max Operating Temperature                              |  | 130   | °C<br>UL 796  |

The data, while believed to be accurate and based on analytical methods considered to be reliable, is for information purposes only. Any sales of these products will be governed by the terms and conditions of the agreement under which they are sold.

[www.isola-group.com/products/all-printed-circuit-materials/is410/](http://www.isola-group.com/products/all-printed-circuit-materials/is410/)

The Isola name and logo are registered trademarks of Isola Corp. USA in the USA and other countries. IS410 is a registered trademark of Isola USA Corp. in the USA. All other trademarks mentioned herein are property of their respective owners.

© 2016, Isola Group, All rights reserved.

